



# Glass Cladding Multi-mode Fibre

## Graded Index Multi-mode Fibre (GIMM)

YOFC silica-cladding multimode fibres with graded index profile are comprehensively optimized at both 850nm and 1300nm operating wavelengths. At both wavelengths, extremely low attenuation and high bandwidth could be achieved. To satisfy the demand of client to the most extent, a series of silica-cladding graded index multimode fibres can be customized with different fibre designs, including core diameter, cladding diameter, fibre diameter and NA.

YOFC fibres are manufactured with the advanced Plasma Activated Chemical Vapor Deposition (PCVD) process. Due to the inherent advantages of the process, YOFC fibres have extremely precise refractive index profiles (RIPs), which could provide excellent geometrical, optical, environmental and mechanical properties.

## Customization Information

- Flexible numerical aperture (NA): 0.14 - 0.3
- Flexible core-cladding diameter ratio (CCDR): 1.05-2.0
- Core diameter: 50 $\mu$ m-1000 $\mu$ m

## Characteristics

- High coupling efficiency to LED and laser sources
- High power transmission
- Good stripping performance
- Low attenuation and high bandwidth

## Applications

- Fibre sensor and laser transmission
- Data communications, local area networks and CATV
- Medical apparatus
- Optical devices and connectors

## Specifications-1

Fibre Type	GI 50/125-20/250	GI 80/125-30/250	GI 100/125-29/250	GI 100/140-29/250	GI 105/125-30/250	GI 100/125-14/250	
Part No.	GI2012-E	GI2017-C	GI2016-F	GI2016-H	GI2017-A	GI2011-A	
<b>Optical Properties</b>							
Numerical Aperture	0.20 ± 0.015	0.30 ± 0.02	0.29 ± 0.02	0.29 ± 0.02	0.30 ± 0.02	0.14 ± 0.02	
Attenuation	@850nm (dB/km)	≤ 2.45	≤ 3.5	≤ 3.5	≤ 3.2	≤ 4.0	≤ 20.0
	@1300nm (dB/km)	≤ 0.6	≤ 0.7	≤ 0.7	≤ 0.8	≤ 1.2	-
Bandwidth	@850nm (MHz·km)	≥ 100	≥ 100	≥ 100	≥ 100	≥ 100	-
	@1300nm (MHz·km)	≥ 200	≥ 200	≥ 200	≥ 200	≥ 200	-
<b>Geometrical Properties</b>							
Core Diameter (μm)	50.0 ± 2.0	80.0 ± 3.0	100.0 ± 3.0	100.0 ± 3.0	105.0 ± 3.0	100.0 ± 3.0	
Cladding Diameter (μm)	125.0 ± 2.0	125.0 ± 2.0	125.0 ± 2.0	140.0 ± 2.0	125.0 ± 2.0	125.0 ± 2.0	
Coating Diameter (μm)	250.0 ± 10.0	250.0 ± 10.0	250.0 ± 10.0	250.0 ± 10.0	250.0 ± 10.0	250.0 ± 10.0	
Core/Cladding Concentricity (μm)	≤ 3.0	≤ 3.0	≤ 3.0	≤ 3.0	≤ 3.0	≤ 3.0	
Core Non-circularity (%)	≤ 2.0	≤ 5.0	≤ 2.0	≤ 3.0	≤ 2.0	≤ 3.0	
Cladding Non-circularity (%)	≤ 1.0	≤ 1.0	≤ 1.0	≤ 1.0	≤ 1.0	≤ 1.0	
<b>Material Composition</b>							
Core	Ge/F Doped Silica Glass						
Cladding	Pure Silica Glass						
Coating	Dual-layer UV-acrylate						
<b>Mechanical Properties</b>							
Proof Test Level (kpsi)	100	100	100	100	100	100	

## Specifications-2

Fibre Type	GI 105/125-24/250	GI 50/80-29/165	GI 300/330-25/500	GI 200/220-22/500	GI 230/250-22/500	
Part No.	GI2014-J	GI2016-C	GI2014-B	GI2013-N	GI2013-P	
<b>Optical Properties</b>						
Numerical Aperture	0.24 ± 0.02	0.29 ± 0.02	0.25 ± 0.02	0.22 ± 0.02	0.22 ± 0.02	
Attenuation	@850nm (dB/km)	≤ 3.5	≤ 4.0	≤ 7.0	≤ 6.0	≤ 5.0
	@1300nm (dB/km)	≤ 1.5	≤ 2.0	-	-	-
Bandwidth	@850nm (MHz·km)	≥ 100	≥ 100	-	-	-
	@1300nm (MHz·km)	≥ 200	≥ 200	-	-	-
<b>Geometrical Properties</b>						
Core Diameter (μm)	105.0 ± 3.0	50.0 ± 3.0	300.0 ± 10.0	200.0 ± 4.0	230.0 ± 5.0	
Cladding Diameter (μm)	125.0 ± 2.0	80.0 ± 2.0	330.0 ± 5.0	220.0 ± 3.0	250.0 ± 5.0	
Coating Diameter (μm)	250.0 ± 10.0	165.0 ± 8.0	500.0 ± 20.0	500.0 ± 20.0	500.0 ± 20.0	
Core/Cladding Concentricity (μm)	≤ 3.0	≤ 3.0	≤ 3.0	≤ 3.0	≤ 3.0	
Core Non-circularity (%)	≤ 2.0	≤ 2.0	-	-	-	
Cladding Non-circularity (%)	≤ 1.0	≤ 1.0	-	-	-	
<b>Material Composition</b>						
Core	Ge/F Doped Silica Glass					
Cladding	Pure Silica Glass					
Coating	Dual-layer UV-acrylate					
<b>Mechanical Properties</b>						
Proof Test Level (kpsi)	100	100	100	100	100	

• 010019 Rev 202205