

Industrial confidentiality

PRODUCT SPECIFICATION

Product code: IXF-2CF-EY-O-12-130-RAD-Gen3

	Parameter	Specification	Units
1	Core diameter	12 ±1	µm
2	Clad diameter	125 ±3	µm
3	Coating diameter	210 ±15	µm
4	Core NA	0.19 ±0.02	
5	Cladding NA	≥0.46	
6	Clad absorption @915nm	2.9 ±0.6	dB/m
7	Clad absorption @976nm*	11.6 ±2.4	dB/m
8	Core absorption @1536nm	60 ±10	dB/m
9	Multimode background losses	<50	dB/km
10	Core-clad offset	<1.0	µm
11	Proof test level	100	kpsi
12	RIGV @1560nm	<0.02	dB/kRad

*: Calculated from 915 nm absorption value

<p>Comments</p> <ul style="list-style-type: none"> Octagonal cladding shape HeNe multimode tested OTDR tested Power Conversion Efficiency (PCE) >40%** RIGV: Radiation Induced Gain Variation <i>RIGV has been measured in amplifier configuration (10W output power) with 915nm backward pumping (fiber length = 6m)</i>
--

** : Following XFS/080301ARL procedure

Effective date of this document: 17/06/2020

Edition: B

Document reference: IXF-2CF-EY-O-12-130-RAD-Gen3_edB.pdf

Specifications are subject to change without notice

PSD-L-Q-E-086-I

