

Parameters

Cutoff Wavelength	1720 ± 80 nm
Attenuation @1950 nm	< 11.5 dB/km
@2000 nm	< 22.5 dB/km
Beat Length @1950 nm	< 5.2 mm
Mode Field Diameter @1950nm	8 ± 1 μm
Numerical Aperture	0.21 ± 0.01
Core/Clad Concentricity	< 1 μm
Cladding Diameter	125 ± 1 μm
Coating Diameter	250 ± 15 μm
Proof Test Level	100 kpsi

Design parameters

Operating Wavelength	1850... 2200 nm
Design	Panda
Holding Parameter @1550 nm	< 1.10 ⁻⁵ m ⁻¹
Coating Material	Dual Acrylate
Operating Temperature Range	-40 to +85°C