

**Parameters**

Cutoff Wavelength	900 ± 50 nm
Attenuation @980 nm	< 2.5 dB/km
Beat Length @980 nm	< 2.3 mm
Mode Field Diameter @980nm	6.6 ± 0.5 μm
Numerical Aperture	0.12 ± 0.01
Core/Clad Concentricity	< 1 μm
Cladding Diameter	125 ± 1 μm
Coating Diameter	250 ± 15 μm
Proof Test Level	100 kpsi

**Design parameters**

Operating Wavelength	980 nm
Design	PANDA
Core Ellipticity	< 15 %
Holding Parameter	< 1.10 <sup>-5</sup> m <sup>-1</sup>
Coating Material	Dual Acrylate
Operating Temperature Range	-40 to +85°C